

US009409147B2

(12) United States Patent

Chiang et al.

(54)

(10) Patent No.: US 9,409,147 B2 (45) Date of Patent: Aug. 9, 2016

METHOD FOR GRANULATION OF
ABSORBENT AND ADSORBENT GRANULES
PREPARED BY THE SAME

(71) Applicant: Institute of Nuclear Energy Research
Atomic Energy Council, Executive
Yuan, Longtan Township, Taoyuan

County (TW)

(72) Inventors: Sheng-Wei Chiang, Longtan Township, Taoyuan County (TW); Kuang-Li
Chien, Longtan Township, Taoyuan
County (TW); Jen-Chieh Chung,
Longtan Township, Taoyuan County
(TW); Shih-Che Huang, Longtan
Township, Taoyuan County (TW);

Chi-Hung Liao, Longtan Township, Taoyuan County (TW); Kou-Min Lin, Longtan Township, Taoyuan County

(TW)

(73) Assignee: INSTITUTE OF NUCLEAR
ENERGY RESEARCH ATOMIC
ENERGY COUNCIL, EXECUTIVE
YUAN, Taoyuan County (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35

U.S.C. 154(b) by 210 days.

(21) Appl. No.: 14/454,448

(22) Filed: Aug. 7, 2014

(65) **Prior Publication Data**

US 2015/0238932 A1 Aug. 27, 2015

(30) Foreign Application Priority Data

Feb. 25, 2014 (TW) 103106269 A

(51)	Int. Cl.	
	B01J 23/00	(2006.01)
	B01J 20/30	(2006.01)
	B01J 47/00	(2006.01)
	R011 20/18	(2006.01)

C02F 1/42	(2006.01)
B01J 20/10	(2006.01)
B01J 20/12	(2006.01)
B01J 20/16	(2006.01)
G21F 9/12	(2006.01)
G21F 9/04	(2006.01)
G21F 9/10	(2006.01)
C02F 101/00	(2006.01)

(52) U.S. Cl.

(58) Field of Classification Search

,	CPC	B01J 23/00			
	USPC				
	See application file for complete search history.				

(56) References Cited

U.S. PATENT DOCUMENTS

8,394,739	B2*	3/2013	Al-Jlil	 B01J 20/12
				210/688

^{*} cited by examiner

Primary Examiner — Edward Johnson (74) Attorney, Agent, or Firm — Muncy, Geissler, Olds & Lowe, P.C.

(57) ABSTRACT

The present invention relates to a method for granulation of an absorbent and adsorbent granules prepared by the same. The method comprises the steps of blending sodium metasilicate, metakaoline and an inorganic ion exchange material in water to form a slurry; decanting the resulted slurry onto a nylon cloth of 300 to 400 meshes and natural drying at ambient temperature to solidification; then breaking the solidified final product and sieving it by a screen having a mesh size of from 0.2 to 2.5 mm to provide the absorbent granules having excellent absorbability.

12 Claims, 1 Drawing Sheet